



Bumperchute® Seam Sealing

- We recommend McNett water based SeamSure. Be sure to check directions on the side of container for specifics before beginning the seam sealing process.
- Seam sealing should be done in a fully ventilated area. Lay the Bumperchute out flat. Taut seams allow for even application and penetration of the sealer.
- Seams on the top of the Bumperchute are the only ones that need to be sealed.
- Apply sealant to the inside and outside of all exposed seams. Draw or brush the sealant along the seam, spreading it evenly and liberally into all of the needle holes (a Q-Tip works well). Several thin layers will work better than one thick layer. Allow 30 minutes to 1 hour for the sealant to completely dry before storing the Bumperchute.

Bumperchute Co.

**8815 SE 74th Place • Mercer Island, WA 98040 • www.bumperchute.com
LOCAL 206-232-8189 • TOLL FREE 1-866-232-8189 • FAX 206-230-4294**